



INTERNATIONAL APPLICATION PUBLISHED UNDER THE PATENT COOPERATION TREATY (PCT)

<p>(51) International Patent Classification ⁶ : C03C 25/02, C08K 5/053, 3/32, 5/57, 5/405, 3/16, 3/30</p>	<p>A1</p>	<p>(11) International Publication Number: WO 99/61384</p> <p>(43) International Publication Date: 2 December 1999 (02.12.99)</p>																								
<p>(21) International Application Number: PCT/US99/10963</p> <p>(22) International Filing Date: 18 May 1999 (18.05.99)</p> <p>(30) Priority Data: 60/087,038 28 May 1998 (28.05.98) US</p> <p>(71) Applicant (for all designated States except US): OWENS CORNING [US/US]; One Owens Corning Parkway, Toledo, OH 43659 (US).</p> <p>(72) Inventors; and (75) Inventors/Applicants (for US only): CHEN, Liang [CN/US]; 7292 Halcyon Place, New Albany, OH 43054 (US). WILLIAMS, Steven, H. [US/US]; 3901 Worthington Road, Alexandria, OH 43001 (US). AGRAWAL, Arun, K. [US/US]; 1872 Stockwell Drive, Columbus, OH 43235 (US). BRANNON, Kathryn, L. [US/US]; 112 Venetian Way, Pataskala, OH 43062 (US).</p> <p>(74) Agents: BARNES, Stephen, W. et al.; Owens Corning Science & Technology Center, Building 54, 2790 Columbus Road, Granville, OH 43023-1200 (US).</p>		<p>(81) Designated States: AL, AM, AT, AU, AZ, BA, BB, BG, BR, BY, CA, CH, CN, CU, CZ, DE, DK, EE, ES, FI, GB, GD, GE, GH, GM, HR, HU, ID, IL, IN, IS, JP, KE, KG, KP, KR, KZ, LC, LK, LR, LS, LT, LU, LV, MD, MG, MK, MN, MW, MX, NO, NZ, PL, PT, RO, RU, SD, SE, SG, SI, SK, SL, TJ, TM, TR, TT, UA, UG, US, UZ, VN, YU, ZW, ARIPO patent (GH, GM, KE, LS, MW, SD, SL, SZ, UG, ZW), Eurasian patent (AM, AZ, BY, KG, KZ, MD, RU, TJ, TM), European patent (AT, BE, CH, CY, DE, DK, ES, FI, FR, GB, GR, IE, IT, LU, MC, NL, PT, SE), OAPI patent (BF, BJ, CF, CG, CI, CM, GA, GN, GW, ML, MR, NE, SN, TD, TG).</p> <p>Published <i>With international search report.</i></p>																								
<p>(54) Title: CORROSION INHIBITING COMPOSITION FOR POLYACRYLIC ACID BASED BINDERS</p> <div style="text-align: center;"> <p>Results of Polarization Resistance Tests of AISI 1018 Steel in the 10% Binder Solution</p> <table border="1"> <caption>Approximate Corrosion Rate (mpy) from Chart</caption> <thead> <tr> <th>Binder/Corrosion Inhibitor</th> <th>75 F (Solid)</th> <th>160 F (Hatched)</th> </tr> </thead> <tbody> <tr> <td>HF-05</td> <td>~300</td> <td>~500</td> </tr> <tr> <td>PAG</td> <td>~1150</td> <td>~100</td> </tr> <tr> <td>HF-05 + Thiourea</td> <td>~50</td> <td>~50</td> </tr> <tr> <td>PAG + Thiourea</td> <td>~380</td> <td>~50</td> </tr> <tr> <td>PAG + Tin Chloride</td> <td>~50</td> <td>~50</td> </tr> <tr> <td>PAG + Tin Oxalate</td> <td>~100</td> <td>~50</td> </tr> <tr> <td>PAG + Tin Sulfate</td> <td>~50</td> <td>~50</td> </tr> </tbody> </table> </div> <p>(57) Abstract</p> <p>A fibrous glass binder that reduces corrosion of polycarboxy based binders, such as polyacrylic acid based binders, on carbon steel. The disclosed binder contains corrosion inhibitors such as tin oxalate, tin sulfate, tin chloride and thiourea.</p>			Binder/Corrosion Inhibitor	75 F (Solid)	160 F (Hatched)	HF-05	~300	~500	PAG	~1150	~100	HF-05 + Thiourea	~50	~50	PAG + Thiourea	~380	~50	PAG + Tin Chloride	~50	~50	PAG + Tin Oxalate	~100	~50	PAG + Tin Sulfate	~50	~50
Binder/Corrosion Inhibitor	75 F (Solid)	160 F (Hatched)																								
HF-05	~300	~500																								
PAG	~1150	~100																								
HF-05 + Thiourea	~50	~50																								
PAG + Thiourea	~380	~50																								
PAG + Tin Chloride	~50	~50																								
PAG + Tin Oxalate	~100	~50																								
PAG + Tin Sulfate	~50	~50																								

FOR THE PURPOSES OF INFORMATION ONLY

Codes used to identify States party to the PCT on the front pages of pamphlets publishing international applications under the PCT.

AL	Albania	ES	Spain	LS	Lesotho	SI	Slovenia
AM	Armenia	FI	Finland	LT	Lithuania	SK	Slovakia
AT	Austria	FR	France	LU	Luxembourg	SN	Senegal
AU	Australia	GA	Gabon	LV	Latvia	SZ	Swaziland
AZ	Azerbaijan	GB	United Kingdom	MC	Monaco	TD	Chad
BA	Bosnia and Herzegovina	GE	Georgia	MD	Republic of Moldova	TG	Togo
BB	Barbados	GH	Ghana	MG	Madagascar	TJ	Tajikistan
BE	Belgium	GN	Guinea	MK	The former Yugoslav Republic of Macedonia	TM	Turkmenistan
BF	Burkina Faso	GR	Greece	ML	Mali	TR	Turkey
BG	Bulgaria	HU	Hungary	MN	Mongolia	TT	Trinidad and Tobago
RJ	Benin	IE	Ireland	MR	Mauritania	UA	Ukraine
BR	Brazil	IL	Israel	MW	Malawi	UG	Uganda
BY	Belarus	IS	Iceland	MX	Mexico	US	United States of America
CA	Canada	IT	Italy	NE	Niger	UZ	Uzbekistan
CF	Central African Republic	JP	Japan	NL	Netherlands	VN	Viet Nam
CG	Congo	KE	Kenya	NO	Norway	YU	Yugoslavia
CH	Switzerland	KG	Kyrgyzstan	NZ	New Zealand	ZW	Zimbabwe
CI	Côte d'Ivoire	KP	Democratic People's Republic of Korea	PL	Poland		
CM	Cameroon	KR	Republic of Korea	PT	Portugal		
CN	China	KZ	Kazakhstan	RO	Romania		
CU	Cuba	LC	Saint Lucia	RU	Russian Federation		
CZ	Czech Republic	LI	Liechtenstein	SD	Sudan		
DE	Germany	LK	Sri Lanka	SE	Sweden		
DK	Denmark	LR	Liberia	SG	Singapore		
EE	Estonia						

CORROSION INHIBITING COMPOSITION FOR POLYACRYLIC ACID BASED BINDERS

TECHNICAL FIELD AND INDUSTRIAL APPLICABILITY OF THE INVENTION

5 The present invention relates to compositions which effectively reduce and or inhibit the corrosion rate of polycarboxy based binders on metal surfaces such as carbon steel. In particular, the invention provides compositions useful for reducing the corrosion rate of polyacrylic acid based binders on carbon steel. The compositions of the invention also provide a method for protecting production steel hardware and machinery from
10 corrosion while also increasing the length of usage for such machinery. The compositions further allow for increases in line productivity since less repairs are required. The compositions and method of the invention are particularly useful in the glass fiber industry in a wide range of products, for example, range insulation, duct board, pipe, ceiling board and commercial and residential insulation.

15

BACKGROUND OF THE INVENTION

Glass fiber comes in various forms and can be used for a variety of applications. During the preparation of glass fiber, whether by blown fiber or continuous filament manufacturing process, the resulting glass fibers are easily degraded in their strength
20 characteristics by the self-abrasive motion of one fiber passing over or interacting with another. As a result of this self-abrasion, surface defects are caused in the glass fiber filaments resulting in reductions in overall mechanical strength. Furthermore, glass fiber which is destined for use as building insulation and sound attenuation is often shipped in a compressed form so as to lower shipping costs. When the compressed bundles of glass
25 fiber are utilized at a job site, it is imperative that the glass fiber product recover a substantial amount of its precompressed thickness; otherwise, loss of insulation and sound attenuation properties may result.

Fibrous glass insulation products generally comprise matted glass fiber bonded together by a cured thermoset polymeric material. Molten streams of glass are drawn into
30 fibers of random lengths and blown into a forming chamber where they are randomly deposited as a mat onto a traveling conveyor. The fibers, while in transit in the forming chamber and while still hot from the drawing operation, are sprayed with an aqueous

binder. A phenol-formaldehyde binder is currently used throughout the fibrous glass insulation industry. The residual heat from the glass fibers and the flow of air through the fibrous mat during the forming operation are generally sufficient to volatilize a majority of the water from the binder, thereby leaving the remaining components of the binder on
5 the fibers as a viscous or semi-viscous high-solids liquid. The coated fibrous mat, which is formed in a compressed state due to the tremendous flow of air through the mat in the forming chamber, is then transferred out of the forming chamber to a transfer zone where the mat vertically expands due to the resiliency of the glass fibers. This vertical expansion is extremely important to the successful manufacture of commercially
10 acceptable fibrous glass thermal or acoustical insulation products. Thereafter, the coated mat is transferred to a curing oven where heated air is blown through the mat to cure the binder and rigidly bond the glass fibers together.

Phenol-formaldehyde binders have been widely used since they have a low viscosity in the uncured state, yet form a rigid thermoset polymeric matrix for the glass
15 fibers when cured. A low binder viscosity in the uncured state is required to allow the maximum vertical expansion of the coated mat when it exits the forming chamber. A binder which forms a rigid matrix when cured is required so that a finished fibrous glass thermal or acoustical insulation product, when compressed for packaging and shipping, will recover to its as-made vertical dimension when installed in a building.

20 Traditionally, fiberglass has been treated with phenol/formaldehyde resole binders to alleviate the previously-mentioned defects. The phenol/formaldehyde binder utilized in the past have typically been the highly alkaline resole type which have the combined advantages of inexpensive manufacture and water solubility. As discussed above, the binders are applied to the fiberglass from aqueous solution shortly after the fibers have
25 been produced, and cured at elevated temperature in a curing oven. Under the curing conditions, any remaining aqueous solvent is evaporated, and the phenol/formaldehyde resole cures to a thermoset state. The fibers in the resulting fiberglass product are thus partially coated with a thin layer of thermoset resin, which tends to accumulate at the junctions where fibers cross each other. The resulting product therefore not only suffers
30 from less self-abrasion, but also exhibits higher recovery than a fiberglass product not incorporating a binder.

The alkaline phenol/formaldehyde resoles contain a fairly large excess of formaldehyde from the manufacturing process. This excess of formaldehyde has been taken advantage of by adding urea to the phenol/formaldehyde resole, resulting in a urea-extended resole. Urea-extended phenol/formaldehyde binders are more cost-effective than the straight phenol/formaldehyde resins, but exhibit some loss in properties as the urea content increases. Thus, efforts have been made to incorporate other resins which can enhance the properties of the binder.

Insulation manufacturers have long desired an alternative polymeric binder system for fibrous glass products. However, low molecular weight, low viscosity binders which allow maximum vertical expansion of the mat in the transfer zone generally cure to form a non-rigid plastic matrix in the finished product, thereby reducing the attainable vertical height recovery of the finished insulation product when installed. Conversely, high viscosity binders which generally cure to form a rigid matrix in the finished product do not allow maximum vertical expansion of the coated, uncured mat. Thus it was desirable to prepare a non-phenol/formaldehyde binder having a low viscosity when uncured and structural rigidity when cured. This was solved in U.S. Patent No. 5,318,990, which is herein incorporated by reference. That patent discloses a fibrous glass binder comprising a polycarboxy polymer, a monomeric trihydric alcohol and a catalyst comprising an alkali metal salt of a phosphorous containing organic acid.

In addition to the obvious improvements gained as a result of the 5,318,990 binder the industry also found that there were further improvements in terms of reducing emissions evolved during the coating and curing processes. To this end, binder formulations utilizing compounds such as polyacrylic acid have been used. Binders such as that are exemplified in U.S. Patent nos. 5,670,585 and 5,538,761, which are herein incorporated by reference.

The use of polyacrylic acid based binders, however, has resulted in severe problems involving high corrosion rates. Thus, there exists a serious need for a method of inhibiting and reducing the corrosion caused by these binder.

SUMMARY OF THE INVENTION

The present invention provides a method and composition that allows for the inhibition and reduction of the corrosive properties of polycarboxy based binders. Prior to the discovery of the present invention, the lifetime of hardware and machinery used with such binders was decreased. In addition productivity levels of manufacturing lines was decreased due to downtime associated with repairs and replacement due to corrosion. As a result of corrosive problems binders with more emissions were used so as to avoid corrosion. However, the present invention allows for the use of the polyacrylic acid based binders, having lower emissions, without the problems associated with corrosion. This results in increases in line productivity as well as reduction in harmful emissions. In some embodiments, the invention reduces harmful end product emissions like cyanate. In addition, the invention may also improve parting strength.

One embodiment of the polyacrylic acid based binder of the invention comprises either thiourea, tin chloride (II), tin sulfate (II), tin oxalate (II) or combinations of the above with a polycarboxy polymer, a monomeric trihydric alcohol, and a catalyst comprising an alkali salt of a phosphorous containing organic acid.

BRIEF DESCRIPTION OF THE DRAWINGS

Figure 1 is a graph demonstrating corrosion rate versus various binders having corrosion inhibitors.

DETAILED DESCRIPTION AND PREFERRED EMBODIMENTS OF THE INVENTION

The binder according to the present invention comprises an aqueous solution of a polycarboxy polymer, a monomeric trihydric alcohol, a catalyst, a pH adjuster and a corrosion inhibitor. The viscosity of the binder is very low, due to the use of the monomeric trihydric alcohol crosslinking agent, and provides a maximized vertical expansion of the fibrous glass mat as it exits the forming chamber; similar to that vertical expansion provided by the well-known phenolformaldehyde binders. Generally, the use of a monomeric reactant in a low viscosity curable resin results in a weak thermoset structure when cured, however the catalyst of the invention allows the formation of a

rigid thermoset when a resin comprising a polycarboxy polymer and a monomeric trihydric alcohol is cured. See U.S. Patent no. 5,318,990.

The polycarboxy polymer of the present invention comprises an organic polymer or oligomer containing more than one pendant carboxy group. The polycarboxy polymer
5 may be a homopolymer or copolymer prepared from unsaturated carboxylic acids including, but not limited to, acrylic acid, methacrylic acid, crotonic acid, isocrotonic acid, maleic acid, cinnamic acid, 2-methylmaleic acid, itaconic acid, 2-methylitaconic acid, a, b-methyleneglutaric acid, and the like. Alternatively, the polycarboxy polymer may be prepared from unsaturated anhydrides including, but not necessarily limited to, maleic
10 anhydride, itaconic anhydride, acrylic anhydride, methacrylic anhydride, and the like, as well as mixtures thereof. Methods for polymerizing these acids and anhydrides are well-known in the chemical art.

The polycarboxy polymer of the present invention may additionally comprise a copolymer of one or more of the aforementioned unsaturated carboxylic acids or
15 anhydrides and one or more vinyl compounds including, but not necessarily limited to, styrene, a-methylstyrene, acrylonitrile, methacrylonitrile, methyl acrylate, ethyl acrylate, n-butyl acrylate, isobutyl acrylate, methyl methacrylate, n-butyl methacrylate, isobutyl methacrylate, glycidyl methacrylate, vinyl methyl ether, vinyl acetate, and the like. Methods for preparing these copolymers are well-known in the art.

Preferred polycarboxy polymers comprise homopolymers and copolymers of the
20 polyacrylic acid. The preferred polyacrylic acid has a molecular weight ranging from about 100 to about 200,000; more preferably from about 1,000 to about 10,000 with about 2,000 to about 6,000 being the most preferred. In addition, the preferred polyacrylic acid has free carboxylic acid groups from greater than about 90% with greater
25 than about 95% being most preferred.

Contemplated equivalent trihydric alcohols according to the present invention having the same operability and utility include, but are not necessarily limited to, glycerol, trimethylolpropane, trimethylolethane, triethanolamine, 1, 2, 4-butanetriol, and the like, as well as mixtures thereof. In practice, the monomeric trihydric alcohols of the
30 present invention may be mixed with other polyhydric alcohols for use in the inventive binder composition. Such other polyhydric alcohols include, but are not necessarily limited to, ethylene, glycol, 1, 3-propanediol, 1, 4-butanediol, 1, 6-hexanediol, 2-butene-

1, erythritol, pentaerythritol, sorbitol, and the like, as well as mixtures thereof.

Preferred monomeric trihydric alcohols comprise glycerol and trimethylolpropane, as well as mixtures thereof. Examples of preferred trihydric alcohols include triethanolamine and glycerine. In a preferred embodiment the glycerine is obtained from Proctor and Gamble and the triethanolamine is obtained from Ashland Chemical.

The catalyst according to the present invention comprises an alkali metal salt of a phosphorous-containing organic acid; particularly alkali metal salts of phosphorous acid, hypophosphorous acid, and polyphosphoric acids. Examples of such catalysts include, but are not necessarily limited to, sodium, sodium phosphite, potassium phosphite, disodium pyrophosphate, tetrasodium pyrophosphate, sodium tripolyphosphate, sodium hexametaphosphate, potassium phosphate, potassium polymetaphosphate, potassium polyphosphate, potassium tripolyphosphate, sodium trimetaphosphate, and sodium tetrametaphosphate, as well as mixtures thereof.

Preferred catalysts include sodium hypophosphite and sodium phosphite, as well as mixtures thereof. In a preferred embodiment, the catalyst is sodium hypophosphite obtained from Oxychem.

The corrosion inhibiting agent of the invention is selected so as to reduce corrosion of acidic solutions. For example, thiourea and other similar sulfur compounds such as allylthiourea are useful inhibitors. Exemplary inhibitors are compounds such as tin oxalate, tin sulfate, tin chloride and thiourea. In a preferred embodiment, the tin oxalate is obtained from Goldschmidt Industrial Chemicals Corp. Preferably, corrosion inhibiting agents are added in amounts ranging from about 100 to about 100,000 ppm. In a particularly preferred embodiments, the amount ranges from about 1,000 to about 5,000 ppm.

The polycarboxy polymer, monomeric trihydric alcohol, catalyst, and corrosion inhibitor may be mixed with water in any conventional mixing device with agitation. The ratio of polycarboxy polymer to monomeric trihydric alcohol may be determined by comparing the ratio of moles of hydroxyl groups contained in the monomeric trihydric alcohol to the moles of carboxy groups contained in the polycarboxy polymer. This stoichiometric ratio may vary over wide limits from about 0.5 to about 1.5. Preferably, the ratio may vary from about 0.7 to about 1.0. One ordinarily skilled in the art will appreciate that the amount of catalyst used may also vary over wide limits depending

upon the temperature at which the binder is cured as well as the time during which the binder is maintained at the elevated curing temperature. Only an amount of a catalyst sufficient to substantially cure the binder (i.e., react together greater than about 75% of the stoichiometrically available carboxy and hydroxyl groups) need be added to the binder mixture. Based upon the combined weight of the polycarboxy polymer, monomeric trihydric alcohol, and catalyst, the amount of catalyst required may vary over wide limits from about 1% to about 15% by weight. Preferably, the amount may vary from about 4% to about 8% by weight. Water may be added to the mixture of polycarboxy polymer, monomeric trihydric alcohol, and catalyst in any amount which would produce an aqueous binder having a viscosity and flow rate suitable for its application to a forming fibrous glass mat by any convenient method, such as by spraying. Conveniently, water may comprise up to about 95% by weight of the binder.

The binders of the present invention may optionally contain conventional adjuvants such as, for example, coupling agents, dyes, oils, fillers, thermal stabilizers, flame retarding agents, lubricants, pH adjusters and the like, in conventional amounts generally not exceeding 20% of the weight of the binder. In particular, pH adjusters such as ammonium hydroxide may be used to raise the pH. The preferred pH for application of the binder is from about 2.5 to about 5 with about 3 to about 4 being the most preferred.

In operation, the inventive binder is applied to glass fibers as they are being produced and formed into a mat, water is volatilized from the binder, and the high-solids binder-coated fibrous glass mat is heated to cure the binder and thereby produce a finished fibrous glass batt which may be used as a thermal or acoustical insulation product, a reinforcement for a subsequently produced composite, etc.

It is generally well-known in the art to produce a porous mat of fibrous glass by fiberizing molten glass and immediately forming a fibrous glass mat on a moving conveyor. Glass is melted in a tank and supplied to a fiber forming device such as a spinner or a bushing. Fibers of glass are attenuated from the device and are blown generally downwardly within a forming chamber. The glass fibers typically have a diameter from about 3 to about 9 microns and have a length from about ¼ inch to about 3 inches. Preferably, the glass fibers range in diameter from about 3.5 to about 7 microns, and have a length from about ½ inch to about 2 inches. The glass fibers are deposited onto a perforated, endless forming conveyor. The binder is applied to the glass fibers as

they are being formed by means of suitable spray applicators so as to result in a distribution of the binder throughout the formed mat of fibrous glass. The glass fibers, having the uncured resinous binder adhered thereto, are gathered and formed into a mat on the endless conveyor within the forming chamber with the aid of a vacuum drawn through the mat from below the forming conveyor. The residual heat contained in the glass fibers as well as the air flow through the mat causes a majority of the water to volatilize from the mat before it exits the forming chamber.

As the high-solids resin-coated fibrous glass mat emerges from the forming chamber, it expands vertically due to the resiliency of the glass fibers. The expanded mat is then conveyed to and through a curing oven wherein heated air is passed through the mat to cure the resin. Flights above and below the mat slightly compresses the mat to give the finished product a predetermined thickness and surface finish. Typically, the curing oven is operated at a temperature from about 200°C to about 350°C. Preferably, the temperature ranges from about 225° to about 300°C. Generally, the mat resides within the oven for a period of time from about 1/4 minute to about 3 minutes. For the manufacture of conventional thermal or acoustical insulation products, the time ranges from about 3/4 minute to about 2 minutes. The fibrous glass having a cured, rigid binder matrix emerges from the oven in the form of a batt which may be compressed for packaging and shipping and which will thereafter substantially fully recover its as-made vertical dimension when unconstrained. By way of example, a fibrous glass mat which is about 1 1/4 inches thick as it exits from the forming chamber, will expand to a vertical thickness of about 9 inches in the transfer zone, and will be slightly compressed to a vertical thickness of about 6 inches in the curing oven.

Example I

The following binders were prepared with and without inhibitors and applied to fibrous glass as it was formed into a mat.

Binder A	Polyacrylic Acid (6000 MW)	69.92%
30	Triethanol amine	22.94%
	Sodium hypophosphite	4.64%

	Ammonia	2.50%
Binder B	CA-4885 (polyacrylic acid - 2000 MW)	70.55%
	Glycerine	21.43%
	Sodium hypophosphite	5.52%
5	Ammonia	2.50 %

The binders were then tested according to Article 15, Part 1120 Combustion Toxicity Testing New York State Uniform Fire Prevention and Building Code by Southwest Research Institute. A 9% LOI sample had a LC50 of 114gm versus the lower
 10 limit of 16gm. In addition, a polarization resistance measurement technique, similar to that described in ASTM Standard Practice G59, was used to estimate the corrosion rates of the carbon steel coupons which were exposed to the binder solutions in the absence or presence of the inhibiting agents. The results are given in Table I below.

15 Table 1: Corrosion Rate (mpy) Comparison at 750°F and 160°F

Binder/Inibitor	75F	160F	Corrosion Inhibitor PPM
Binder A	280	480	--
Binder B	113	1152	--
A + Thiourea	<1	48	1000
B + Thiourea	2	363	1000
B + Tin Chloride	46	48	5000
B + Tin Oxalate	1	99	1000
B + Tin Sulfate	1	80	1000


In addition to testing for corrosion inhibition, the hydrogen cyanide levels generated in the air stream were also measured to be approximately 1-2ppm regardless of the amount of sample in the range of from 50 to 150 grams. (The upper limit for
 20 compliance is approximately 150 ppm in a 30 minute period.)

When tested, some range insulation products produced using binder B plus either the tin oxalate, tin sulfate or thiourea corrosion inhibitor showed improvements in parting strength ranging from 1.4x to 3x versus a standard.

WHAT IS CLAIMED IS

1. A fibrous glass binder, comprising an aqueous solution of:
 - a) a polycarboxy polymer comprising a homopolymer or copolymer prepared
5 from an unsaturated carboxylic acid or an anhydride or mixtures thereof;
 - b) a monomeric trihydric alcohol;
 - c) a catalyst, comprising an alkali metal salt of a phosphorous-containing organic acid; and
 - d) a corrosion inhibiting agent.
- 10 2. The fibrous glass binder according to claim 1, wherein the polycarboxy polymer comprises homopolymers and copolymers of polyacrylic acid.
3. The fibrous glass binder according to claim 1, wherein the monomeric trihydric
15 alcohol comprises glycerine.
4. The fibrous glass binder according to claim 1, wherein the catalyst is selected from the group consisting essentially of sodium hypophosphite and sodium phosphite, and mixtures thereof.
- 20 5. The fibrous glass binder of claim 1, wherein the corrosion inhibiting agent is selected from the group consisting of tin oxalate, tin sulfate, tin chloride and thiourea.
6. A method for reducing corrosive properties of polycarboxy polymer based binders
25 on carbon steel, comprising:
 - a) adding a corrosion inhibiting agent to a polycarboxy polymer based binder.
7. The method of claim 6, wherein said corrosion inhibiting agent is selected from the group consisting of tin oxalate, tin sulfate, tin chloride and thiourea.
- 30 8. A low corrosion process for the preparation of a binder coated glass fiber product comprising:

- 5 a) selecting a polycarboxy polymer, a monomeric trihydric alcohol, and a catalyst, as components of the binder;
- b) mixing said components;
- c) applying to said binder components a corrosion inhibiting agent;
- d) applying the mixture comprising (a) and (c) to glass fibers in need of binder coating in order to form a binder containing glass fiber; and
- e) curing said binder containing glass fibers to form a binder coated glass fiber product.
- 10 9. A process for preparation of a binder coated glass fiber product having low cyanate emissions comprising:
- a) selecting a polycarboxy polymer, a monomeric trihydric alcohol, and a catalyst, as components of the binder;
- b) mixing said components;
- 15 c) adding to said binder components a corrosion inhibiting agent selected from the group consisting of tin oxalate, tin sulfate, and tin chloride;
- d) applying the mixture comprising (a) and (c) to glass fibers in need of binder coating in order to form a binder containing glass fiber; and
- e) curing said binder containing glass fibers to form a binder coated glass
- 20 fiber product.
10. The process of claim 9, wherein said monomeric trihydric alcohol is glycerine.



INTERNATIONAL SEARCH REPORT

International Application No

PLI/US 99/10963

A. CLASSIFICATION OF SUBJECT MATTER

IPC 6 C03C25/02 C08K5/053 C08K3/32 C08K5/57 C08K5/405
C08K3/16 C08K3/30

According to International Patent Classification (IPC) or to both national classification and IPC

B. FIELDS SEARCHED

Minimum documentation searched (classification system followed by classification symbols)

IPC 6 C03C C08K

Documentation searched other than minimum documentation to the extent that such documents are included in the fields searched

Electronic data base consulted during the international search (name of data base and, where practical, search terms used)

DOSYS BOCA FSTA EUREG

C. DOCUMENTS CONSIDERED TO BE RELEVANT

Category *	Citation of document, with indication, where appropriate, of the relevant passages	Relevant to claim No.
A	US 5 318 990 A (STRAUSS CARL R) 7 June 1994 (1994-06-07) cited in the application the whole document ---	1-10
A	US 3 374 200 A (DEICHERT WILLIAM GEORGE) 19 March 1968 (1968-03-19) the whole document ---	1-10
A	US 4 598 119 A (VOLK HENRY) 1 July 1986 (1986-07-01) column 1, line 47 - column 2, line 11 --- -/--	1-10

☒ Further documents are listed in the continuation of box C.

☒ Patent family members are listed in annex.

* Special categories of cited documents:

"A" document defining the general state of the art which is not considered to be of particular relevance

"E" earlier document but published on or after the international filing date

"L" document which may throw doubts on priority claim(s) or which is cited to establish the publication date of another citation or other special reason (as specified)

"O" document referring to an oral disclosure, use, exhibition or other means

"P" document published prior to the international filing date but later than the priority date claimed

"T" later document published after the international filing date or priority date and not in conflict with the application but cited to understand the principle or theory underlying the invention

"X" document of particular relevance; the claimed invention cannot be considered novel or cannot be considered to involve an inventive step when the document is taken alone

"Y" document of particular relevance; the claimed invention cannot be considered to involve an inventive step when the document is combined with one or more other such documents, such combination being obvious to a person skilled in the art.

"&" document member of the same patent family

Date of the actual completion of the international search

9 September 1999

Date of mailing of the international search report

17/09/1999

Name and mailing address of the ISA

European Patent Office, P.B. 5818 Patentlaan 2
NL - 2280 HV Rijswijk
Tel. (+31-70) 340-2040, Tx. 31 651 epo nl,
Fax: (+31-70) 340-3016

Authorized officer

Van Bommel, L

INTERNATIONAL SEARCH REPORT

International Application No

PCT/US 99/10963

C.(Continuation) DOCUMENTS CONSIDERED TO BE RELEVANT

Category *	Citation of document, with indication, where appropriate, of the relevant passages	Relevant to claim No.
A	<p> DATABASE WPI Section Ch, Week 8051 Derwent Publications Ltd., London, GB; Class A82, AN 80-90988C XP002114843 & JP 55 140740 A (DAI-ICHI KASEI KK), 4 November 1980 (1980-11-04) abstract ----- </p>	1-10

INTERNATIONAL SEARCH REPORT

Information on patent family members

International Application No

PCT/US 99/10963

Patent document cited in search report		Publication date	Patent family member(s)	Publication date
US 5318990	A	07-06-1994	NONE	
US 3374200	A	19-03-1968	NONE	
US 4598119	A	01-07-1986	NONE	
JP 55140740	A	04-11-1980	NONE	